



TECHNICAL DATA SHEET

SK2TR250-3

Internal mould release agent

► DESCRIPTION

Additive SK2TR250-3 is a liquid internal release agent used in the processing of composites. Ideally, the use of external release agents can be reduced significantly. Any post-moulding operation can be performed without further steps. As a consequence, the use of SK2TR250-3 results in an excellent overall economy. The product will not have an influence on the chemical and physical properties of the resin and does not contain any silicones or waxes. SK2TR250-3 is used as internal release agent for polyester resins.

This product is used in various manufacturing processes of parts made of composite materials.

► APPLICATION

Additive SK2TR250-3 is added directly into the resin. To achieve best release performance, thorough and careful admixing of the product is crucial. The recommended dosage varies depending on the formulation and the raw materials between 0.5 % and 1 % relative to the amount of resin. The adequate concentration has to be identified by individual on-site trials. Please contact our technical service for assistance. It is advisable to start the tests with the lowest recommended level and to increase the dosage until the desired results are achieved. Prior to the first application of SK2TR250-3, the moulds have to be cleaned from residues of dirt and release agents. Afterwards it is recommended to apply a mould sealer and to support the initial release by the single use of an external release agent. For these purposes we recommend the use of cleaner and sealers from the category SK2TR.

► TECHNICAL DATA

Appearance:	Colourless liquid
Composition:	Mixture of active substances and high molecular hydrocarbons
Density [g/cm ³]:	Approx. 0.85
Flashpoint [°C]:	200 °C

► SIZE

Packaging
Can of 25 kg
Drum of 160 kg



TECHNICAL DATA SHEET

SK2TR250-3

Internal mould release agent

► STORAGE

The product should be stored in tightly sealed containers and has to be protected from frost, heat and direct sunlight. If these rules are obeyed, the product can be stored for at least 24 months.