



This medium weight non-woven polyamide breather could be used for high pressure curing. It is stretchable and has good drapability.

This product is used in various manufacturing processes of parts made of composite materials.

TECHNICAL DATA	VALUE
Material type:	Polyamide 6.6
Weight:	230 g/m ²
Recommended curing pressure*	< 7 Bar
Maximum use temperature*	230°C
Color:	White
Fibre thickness:	17dtex

THICKNESS	WIDTH	LENGTH
4-5 mm	1500 mm	50 m

STORAGE

Shelf life: not limited.
Storage conditions: it is recommended to store at temperature from -20°C until +30°C in the original packing.

NOTES

Other widths are available on special order.
Max. width is 2.4 m.
* Maximum use pressure and temperature should be determined under your actual process conditions.