



SK2PP232-1

High-tenacity un-dyed, scoured and heat set peel ply

SK2PP232-1 is a high-tenacity, highly drapable polyamide peel ply without silicon coating used to texture the surface of a composite laminate. The clean, textured surface after using the peel ply allows the secondary bonding or painting. SK2PP232-1 peel ply may reduce or eliminate the need for sanding or abrading of the surface of a composite part. The peel ply is made of high-tenacity polyamide fiber.

This product is used in various manufacturing processes of parts made of composite materials.

TECHNICAL DATA	VALUE	STANDARD
Material type	Polyamide 66	
Color	White	
Surface weight	139 g/m ² ± 5%	GB/T4669-2008
Maximum use temperature*	232°C	

SIZE

Width	1524 mm
Length	229 m

STORAGE

Shelf life: unlimited.

Storage conditions: it is recommended to store at temperatures between -20°C and +30°C in original packing

NOTES

Other width or special sizes available on request.

* Maximum use temperature should be determined in actual process conditions. The maximum use temperature depends on the duration at maximum temperature and is process specific, we recommend testing prior to use.