



SK2BB190-4 is an economic, heavy, non-woven polyester breather partly made from secondary material fibers. It can be used for debulking and autoclave processes. The breather is stretchable and has good drapability for complex shapes.

This product is used in various manufacturing processes of parts made of composite materials.



TECHNICAL DATA	VALUE
Material type:	Polyester
Weight:	340 g/m <sup>2</sup>
Recommended curing pressure*	< 7 Bar
Maximum use temperature*	190°C
Color:	White
Fibre thickness:	17dtex

WIDTH	LENGTH
2000mm	400m

**STORAGE**

Shelf life: not limited.  
Storage conditions: it is recommended to store at temperature from -20°C until +30°C in the original packing.

**NOTES**

Other sizes are available on special order.  
\* Maximum use pressure and temperature should be determined under your actual process conditions.