



SK2VF200-5 is a coextruded mononylon vacuum bagging film, developed to improve softness during handling. This film is suitable for contact with phenolic resins and can be used for oven and autoclave cure temperatures up to 204°C.



TECHNICAL DATA	VALUE	TEST METHOD
Material	Nylon	
Color	Purple	—
Tensile strength at break*	108 MPa	ASTM D882
Elongation at break*	390%	ASTM D882
Maximum use temperature	204°C	—

STORAGE

Shelf life: unlimited.

Storage conditions: store at 10–30°C in original packaging, shielded from direct sunlight and heat sources

NOTES

Thickness: 50µm

Lay flat width / Folding shapes:
 up to 2300mm – LFT
 up to 2300/4600mm – CF

The values given in this TDS are average measurements; a standard tolerance of ±15% applies to all stated figures

* MD unless specified